

Certified according to DIN EN ISO 9001/14001

Examination of a door with regard to the emissions of formaldehyde and volatile organic compounds (VOC) respecting an evaluation in accordance with the French regulations for VOC emissions of construction products (2009/0701/F and 2009/0702/F).

Client: Türelemente Borne Handelsgesellschaft mbH,
54311 Trierweiler

Test report: 3031007A_Grenelle

Commission dated: 2011-08-22

Sample: Door "Fila V" white, lacquered

Date of production: 2011-08-22

Sample received on: 2011-08-24

Testing period: 2011-09-28 to 2011-10-05

Final Classification: A+

Except when otherwise approved / licensed by LGA this test report may only be published and used in unabbreviated original phrasing and form. The test report contains the result of one single examination of the individual test sample and does not represent any universally valid evaluation of the qualities of all products from serial production. Should the content of the test report need any interpretation the German text shall be leading.

T:\Softlines\LFGB_Konsumgueter\2011\Aufträge
Nürnberg\EMISSIONSPRÜFUNG\KUNDEN\Borne\Berichte\2011\3031007A_Grenelle.doc // Page 1 of 3

TÜV Rheinland LGA Products GmbH • Emission Testing
Tillystraße 2 • 90431 Nürnberg, Germany
Tel. +49 (0) 911 655-5445 • Fax +49 (0) 911 655-5603
E-Mail: christine.kuehn@de.tuv.com • <http://www.tuv.com/safety>

Company register Nuremberg HRB 26013
Managing Directors: Dipl.-Ing. Jörg Mähler,
Dipl.-Kfm. Dr. Jörg Schlösser
Tax No. 216/5715/1213 VAT ID No. DE811835490

No. 3031007A_Grenelle

1. Commission

TÜV Rheinland LGA Products GmbH was commissioned to examine a door according to the French regulations for VOC emissions of construction products (2009/0701/F and 2009/0702/F) from the "Ministry of Ecology, Energy, Sustainable Development and Sea".

2. Testing methods

2.1 Testing conditions:

Chamber volume:	1 m ³
Temperature:	(23 ± 2) °C
Relative air humidity:	50 % rel. h. ± 5 % rel. h.
Air velocity:	0.1 to 0.3 m/s
Loading factor for a door:	0,05 m ² /m ³ ± 0.005 m ² /m ³
Air exchange:	0.5 h ⁻¹ ± 0.01 h ⁻¹

The sample was placed in the test chamber on September 28, 2011 for seven days. Sampling was performed after seven days.

2.2 Testing methods

ISO 16000-3: Indoor air – Part 3: Determination of formaldehyde and other carbonyl compounds – Active sampling method

ISO 16000-6: Indoor air – Part 6: Determination of volatile organic compounds in indoor and test chamber air by active sampling on Tenax TA sorbent, thermal desorption and gas chromatography using MS/FID

EN ISO 16000-9: Indoor air – Part 9: Determination of the emission of volatile organic compounds from building products and furnishing – Emission test chamber method

EN ISO 16000-11: Indoor air – Part 11: Determination of the emission of volatile organic compounds from building products and furnishing – Sampling, storage of samples and preparation of test specimens

No. 3031007A_Grenelle

3. Examination results

3.1 Emissions of volatile organic compounds (VOC) ¹

Table 1: Comparison of the requirements of the French regulations with the test results (emissions of VOC ¹ in µg/m³)

Parameters	CAS No.	Requirements of the Emission Classes				Test results after seven days	Emission Class
		A+	A	B	C		
Formaldehyde	50-00-0	< 10	< 60	< 120	> 120	8.7	A+
Acetaldehyde	75-07-0	< 200	< 300	< 400	> 400	3.7	A+
Toluene	108-88-3	< 300	< 450	< 600	> 600	n.d. ³	A+
Tetrachloroethylene	127-18-4	< 250	< 350	< 500	> 500	n.d. ³	A+
Xylene	1330-20-7	< 200	< 300	< 400	> 400	n.d. ³	A+
1,2,4-Trimethylbenzene	95-63-6	< 1,000	< 1,500	< 2,000	> 2,000	n.d. ³	A+
1,4-Dichlorobenzene	106-46-7	< 60	< 90	< 120	> 120	n.d. ³	A+
Ethylbenzene	100-41-4	< 750	< 1,000	< 1,500	> 1,500	n.d. ³	A+
2-Butoxyethanol	111-76-2	< 1,000	< 1,500	< 2,000	> 2,000	n.d. ³	A+
Styrene	100-42-5	< 250	< 350	< 500	> 500	n.d. ³	A+
TVOC ²	- / -	< 1,000	< 1,500	< 2,000	> 2,000	26	A+

¹ VOC = volatile organic compounds

² TVOC = total volatile organic compounds within retention range of C₆ – C₁₆

³ n.d. = not detected, no substances of the corresponding category have been detected, limit of quantification 1 µg/m³

* The substances benzene and dibutylphthalate were not detected in the test chamber (French regulation 2009/0104/F)

4. Evaluation

Final classification for doors, white, lacquered:


Émissions dans l'air intérieur: **A+**

Nuremberg, 2011-11-03

TÜV Rheinland LGA Products GmbH
 LFGB / Consumer Products – Emission Testing


 Dr. Christian Schelle
 Chemist

Person in charge:


 Christine Kühn